



Internet: [www.awqc.com.au](http://www.awqc.com.au)

Email: [producttesting@awqc.com.au](mailto:producttesting@awqc.com.au)

## FINAL REPORT

Report ID : 311761

### Report Information

**Submitting Organisation :** 00109358 : Parchem Construction Supplies Pty Ltd  
**Account :** 130335 : Parchem Construction Supplies Pty Ltd  
**AWQC Reference :** 130335-2020-CSR-16 : Prod Test: Fosroc Renderoc HB70  
**Project Reference :** PT-4554  
**Product Designation :** Fosroc Renderoc HB70  
**Composition of Product :** Cementitious.  
**Product Manufacturer :** Parchem Construction Supplies, Wyong, NSW, AUSTRALIA.  
**Use of Product :** In-Line/Cementitious Repair Mortar.  
**Sample Selection:** As provided by the submitting organisation.  
**Testing Requested :** **AS/NZS 4020 TESTING OF PRODUCTS FOR USE IN CONTACT WITH DRINKING WATER**  
**Product Type :** Composite  
**Samples :** Samples were prepared and controlled as described in Appendix A of AS/NZS 4020:2018  
**Extracts :** Extracts were prepared as described in Appendix/Clause C, D, E, F, G, H, 6.8.  
**Project Completion Date :** 18-Jun-2021  
**Project Comment :** Product sample received in the week 15-Feb-2021; testing commenced 29-Mar-2021.

PLEASE NOTE THAT THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL

THE RESULTS STATED IN THIS REPORT RELATE TO THE SAMPLE OF THE PRODUCT SUBMITTED FOR TESTING. ANY CHANGES IN THE MATERIAL FORMULATION, PROCESS OF MANUFACTURE, THE METHOD OF APPLICATION, OR THE SURFACE AREA-TO-VOLUME RATIO IN THE END USE, COULD AFFECT THE SUITABILITY OF THE PRODUCT FOR USE IN CONTACT WITH DRINKING WATER

Michael Glasson  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025



**FINAL REPORT**

Report ID : 311761

**Summary of Results**

APPENDIX/CLAUSE	RESULTS
C – Taste	Passed at an exposure of 15000 mm <sup>2</sup> per Litre.
D – Appearance	Passed at an exposure of 15000 mm <sup>2</sup> per Litre.
E – Growth of Aquatic Micro-organisms	Passed at an exposure of 15000 mm <sup>2</sup> per Litre.
F – Cytotoxic Activity	Passed at an exposure of 15000 mm <sup>2</sup> per Litre.
G – Mutagenic Activity	Passed at an exposure of 15000 mm <sup>2</sup> per Litre.
H – Metals	Passed at an exposure of 15000 mm <sup>2</sup> per Litre.
6.8 – Organic Compounds	Passed at an exposure of 15000 mm <sup>2</sup> per Litre.

**Test Methods**

Test(s) in Appendix	AWQC Test Method	Reference Method
C	T0320-01	AS/NZS 4020:2018
D	TO029-01 & TO018-01	APHA 2120c & APHA 2130b
E	TO014-03	APHA 4500 O G
F	TM-001	AS/NZS 4020:2018
G	TM-002	AS/NZS 4020:2018
H	TIC-006	EPA 200.8

**Organic Test Methods**

Test(s) in Clause	Test Method	Reference Method
Clause 6.8	TMZ-M36	USEPA524.2
	EP239	USEPA521
	EP132-LL	USEPA_SW846-8270D
	EP075C	USEPA_SW846-8270D
	EP075ASIM	USEPA_SW846-8270D

**Summary Comment :**

The compound was applied (to glass slides) and cured for 7 days at 20°C prior to testing (ratio of 200g to 29mL of drinking water). Twenty four sequential soakings performed to obtain a pH < 9.0. In accordance with section A8 (Cementitious Products).



Internet: [www.awqc.com.au](http://www.awqc.com.au)

Email: [producttesting@awqc.com.au](mailto:producttesting@awqc.com.au)

## FINAL REPORT

Report ID : 311761

### CLAUSE 6.2 Taste

<b>Sample Description</b>	The sample consisted of two coated panels (each coated to one side) with dimensions 75 mm x 100 mm and providing a total surface area of approximately 15000 mm <sup>2</sup> /L. Extracts were prepared using 1000 mL volumes of pre-conditioning water(AI 12.6).
<b>Extraction Temperature</b>	20°C ± 2°C.
<b>Test Method</b>	Taste (Appendix C)
<b>Test Information</b>	
<b>Scaling Factor</b>	Not applicable.
<b>Results</b>	Not detected (sample and controls).
<b>Evaluation</b>	The product passed the requirements of clause 6.2 when tested at an exposure of 15000 mm <sup>2</sup> per Litre.
<b>Number of Samples</b>	2.
<b>Test Comment</b>	The 24 hour extracts were not analysed in this test.

Peter Christopoulos  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025





Internet: [www.awqc.com.au](http://www.awqc.com.au)

Email: [producttesting@awqc.com.au](mailto:producttesting@awqc.com.au)

**FINAL REPORT**

Report ID : 311761

**CLAUSE 6.3 Appearance**

**Sample Description** The sample consisted of two coated panels (each coated to one side) with dimensions 75 mm x 100 mm and providing a total surface area of approximately 15000 mm<sup>2</sup>/L. Extracts were prepared using 1000 mL volumes of pre-conditioning water(AI 12.6).

**Extraction Temperature** 20°C ± 2°C.

**Test Method** Appearance (Appendix D)

**Scaling Factor** Not applicable.

**Results**

	<u>Test (- Blank)</u>	<u>Maximum Allowed</u>	<u>Units</u>
Colour	1	5	HU
Turbidity	<0.1	0.5	NTU

**Evaluation** The product passed the requirements of clause 6.3 when tested at an exposure of 15000 mm<sup>2</sup> per Litre.

**Number of Samples** 1.

**Test Comment** Not applicable.

Andrew Ford  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025





Internet: [www.awqc.com.au](http://www.awqc.com.au)

Email: [producttesting@awqc.com.au](mailto:producttesting@awqc.com.au)

**FINAL REPORT**

Report ID : 311761

**CLAUSE 6.4 Growth of Aquatic Micro-organisms**

**Sample Description** The sample consisted of two coated panels (each coated to one side) with dimensions 75 mm x 100 mm and providing a total surface area of approximately 15000 mm<sup>2</sup>/L. Extracts were prepared using 1000 mL volumes of test water.

**Test Method** Growth of Aquatic Micro-organisms (Appendix E)

**Inoculum** The volume of the inoculum was 100 mL

**Scaling Factor** Not applicable.

**Results**

Mean Dissolved Oxygen	Control	7.2 mg/L
Mean Dissolved Oxygen Difference	Positive Reference	4.5 mg/L
	Negative Reference	0.1 mg/L
	Test	0.10 mg/L

**Evaluation** The product passed the requirements of clause 6.4 when tested at an exposure of 15000 mm<sup>2</sup> per Litre.

**Number of Samples** 1.

**Test Comment** Not applicable.

Thuy Diep  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025





Internet: [www.awqc.com.au](http://www.awqc.com.au)

Email: [producttesting@awqc.com.au](mailto:producttesting@awqc.com.au)

## FINAL REPORT

Report ID : 311761

### CLAUSE 6.5 Cytotoxic Activity

<b>Sample Description</b>	The sample consisted of two coated panels (each coated to one side) with dimensions 75 mm x 100 mm and providing a total surface area of approximately 15000 mm <sup>2</sup> /L. Extracts were prepared using 1000 mL volumes of pre-conditioning water(AI 12.6).
<b>Extraction Temperature</b>	20°C ± 2°C.
<b>Test Method</b>	Cytotoxic Activity (Appendix F)
<b>Scaling Factor</b>	Not applicable.
<b>Results</b>	Non-Cytotoxic (sample and controls).
<b>Evaluation</b>	The product passed the requirements of clause 6.5 when tested at an exposure of 15000 mm <sup>2</sup> per Litre.
<b>Number of Samples</b>	1.
<b>Test Comment</b>	The test extracts and blank extracts were used to prepare nutrient growth medium and subsequently used to grow a cell line (ATCC Number CCL 81) in the analysis. In addition zinc sulphate (0.4 mmol) was used for the positive control in the analysis.

Mira Maric

APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025





Internet: [www.awqc.com.au](http://www.awqc.com.au)

Email: [producttesting@awqc.com.au](mailto:producttesting@awqc.com.au)

## FINAL REPORT

Report ID : 311761

### CLAUSE 6.6 Mutagenic Activity

**Sample Description** The sample consisted of two coated panels (each coated to one side) with dimensions 75 mm x 100 mm and providing a total surface area of approximately 15000 mm<sup>2</sup>/L. Extracts were prepared using 1000 mL volumes of pre-conditioning water(AI 12.6).

**Extraction Temperature** 20°C ± 2°C.

**Test Method** Mutagenic Activity (Appendix G)

**Scaling Factor** Not applicable.

#### Results

	<u>Bacteria Strain</u>		<u>Number of Revertants per Plate</u>			
	S9	Blank	Sample Extract	Positive Controls		
<i>Salmonella typhimurium</i> TA98	-	35, 35, 20	23, 30, 26	3237, 3751, 3787	<u>NPD</u> (20µg)	
Mean ± Standard deviation		30.0 ± 8.7	26.3 ± 3.5	3591.7 ± 307.7		
	+	29, 26, 29	29, 29, 28	3089, 3388, 3697	<u>2-AF</u> (20µg)	
Mean ± Standard deviation		28.0 ± 1.7	28.7 ± 0.6	3391.3 ± 304.0		
<i>Salmonella typhimurium</i> TA102	-	427, 447, 446	385, 458, 579	4903, 5263, 2855	<u>Mitomycin C</u> (10µg)	
Mean ± Standard deviation		440.0 ± 11.3	474.0 ± 98.0	4340.3 ± 1298.9		
	+	540, 552, 564	584, 534, 452	2316, 1756, 2038		
Mean ± Standard deviation		552.0 ± 12.0	523.3 ± 66.6	2036.7 ± 280.0		

**Comments** S9 was used as the metabolic activator. NPD (4-nitro-o-phenylenediamine) and Mitomycin C are specific positive controls for strains TA98 - and TA102 (- and +) respectively, while 2-AF (2-aminofluorene) when used in conjunction with S9 is a positive control for TA98+.

**Evaluation** The product passed the requirements of clause 6.6 when tested at an exposure of 15000 mm<sup>2</sup> per Litre.

**Number of Samples** 1.

**Test Comment** The differences in the mean number of revertants between the blank and test extracts do not exceed two standard deviations; accordingly there is no evidence of a mutagenic response.

Peter Christopoulos  
APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025



**FINAL REPORT**

Report ID : 311761

**CLAUSE 6.7**

**Metals**

**Sample Description**

The sample consisted of two coated panels (each coated to one side) with dimensions 75 mm x 100 mm and providing a total surface area of approximately 15000 mm<sup>2</sup>/L. Extracts were prepared using 1000 mL volumes of pre-conditioning water(AI 12.6).

**Extraction Temperature**

20°C ± 2°C.

**Test Method**

Metals (Appendix H)

**Scaling Factor**

Not applicable.

**Method of Analysis**

All methods used to determine concentrations of metals are based on those described in the US EPA method 200.8 Determination of Trace elements in Waters and Wastes by Inductively Coupled Plasma - Mass Spectrometry. The methods have been adapted for the instrumentation in use at the Australian Water Quality Centre.

Concentration of the metals described in Table 2 of the AS/NZS 4020:2018 are determined as follows:

Aluminium, Antimony, Arsenic, Barium, Boron, Cadmium, Chromium, Copper, Iron, Lead, Manganese, Mercury, Molybdenum, Nickel, Selenium and Silver by Inductively Coupled Plasma Mass Spectrometry.

Results	Limit of Reporting mg/L	Blank mg/L	Test 1 mg/L	Test 2 mg/L	Max Allowed mg/L
<b>Final Extract</b>					
Aluminium	0.001	0.034	0.033	0.038	0.2
Antimony	0.0005	<0.0005	<0.0005	<0.0005	0.003
Arsenic	0.0003	<0.0003	<0.0003	0.0003	0.01
Barium	0.0005	0.0244	0.0234	0.0239	0.7
Boron	0.020	0.091	0.077	0.062	1.4
Cadmium	0.0001	<0.0001	<0.0001	<0.0001	0.002
Chromium	0.0001	0.0002	0.0003	0.0003	0.05
Copper	0.0001	0.0696	0.0702	0.0696	2.0
Iron	0.0005	0.0081	0.0061	0.0068	0.3
Lead	0.0001	0.0004	0.0003	0.0003	0.01
Manganese	0.0001	0.0025	0.0017	0.0018	0.1
Mercury	0.00003	<0.00003	<0.00003	<0.00003	0.001
Molybdenum	0.0001	0.0002	0.0003	0.0002	0.05
Nickel	0.0001	0.0007	0.0005	0.0005	0.02
Selenium	0.0001	<0.0001	<0.0001	<0.0001	0.01
Silver	0.00003	<0.00003	<0.00003	<0.00003	0.1

**Evaluation**

The product passed the requirements of clause 6.7 when tested at an exposure of 42000 mm<sup>2</sup> per Litre.

**Number of Samples**

1.

**Test Comment**

Not applicable.



Dzung Bui

APPROVED SIGNATORY



Corporate Accreditation No.1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025





**FINAL REPORT**

Report ID : 311761

**CLAUSE 6.8 Organic Compounds**

**Sample Description** The sample consisted of two coated panels (each coated to one side) with dimensions 75 mm x 100 mm and providing a total surface area of approximately 15000 mm<sup>2</sup>/L. Extracts were prepared using 1000 mL volumes of pre-conditioning water(AI 12.6).

**Extraction Temperature** 20°C ± 2°C.

**Test Method** Organic Compounds (Clause 6.8). Max Allowed values are taken from the Australian Drinking Water Guidelines and Drinking-water Standards for New Zealand. Please note, some reported compounds have no guideline value.

**Scaling Factor** Not applicable.

**Results**

**Organic Compound**

<b>Nitrosamines</b>	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2107842	ES2107842	
1-Nitrosopiperidine (NPip)	<0.003	<0.003	
1-Nitrosopyrrolidine (NPyr)	<0.01	<0.01	
Nitrosomorpholine (NMor)	<0.003	<0.003	
N-Nitrosodiethylamine (NDEA)	<0.01	<0.01	
N-Nitrosodimethylamine (NDMA)	<0.003	<0.003	0.1 µg/L
N-Nitrosodi-n-propylamine (NDPA)	<0.003	<0.003	
N-Nitrosomethylethylamine (NMEA)	<0.003	<0.003	

**Organic Compound**

<b>Phenols</b>	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2107842	ES2107842	
2 4 5-trichlorophenol	<1.0	<1.0	
2 4 6-trichlorophenol	<1.0	<1.0	20 µg/L
2 4-dichlorophenol	<1.0	<1.0	200 µg/L
2 4-dimethylphenol	<1.0	<1.0	
2 6-dichlorophenol	<1.0	<1.0	
2-chlorophenol	<1.0	<1.0	300 µg/L
2-nitrophenol	<1.0	<1.0	
4-chloro-3-methylphenol	<1.0	<1.0	
m+p cresol	<2.0	<2.0	
o-cresol	<1.0	<1.0	
pentachlorophenol	<2.0	<2.0	9 µg/L
phenol	<1.0	<1.0	



Internet: [www.awqc.com.au](http://www.awqc.com.au)

Email: [producttesting@awqc.com.au](mailto:producttesting@awqc.com.au)

**FINAL REPORT**

Report ID : 311761

**Organic Compound**

Phthalate Esters	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2107842	ES2107842	
Bis(2-ethylhexyl) phthalate	<10	<10	10 µg/L
Butyl benzyl phthalate	<2	<2	
Di(2-ethylhexyl) adipate	<2	<2	
Diethyl phthalate	<2	<2	
Dimethyl phthalate	<2	<2	
Di-n-butyl phthalate	<2	<2	
Di-n-octyl phthalate	<2	<2	

**Organic Compound**

Polycyclic Aromatic Hydrocarbons	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2107842	ES2107842	
Acenaphthene	<0.02	<0.02	
Acenaphthylene	<0.02	<0.02	
Anthracene	<0.02	<0.02	
Benzo(a)anthracene	<0.02	<0.02	
Benzo(a)pyrene	<0.005	<0.005	0.01 µg/L
Benzo(a)pyrene TEQ	<0.005	<0.005	
Benzo(b+j)fluoranthene	<0.02	<0.02	
Benzo(ghi)perylene	<0.02	<0.02	
Benzo(k)fluoranthene	<0.02	<0.02	
Chrysene	<0.02	<0.02	
Dibenzo(a-h)anthracene	<0.02	<0.02	
Fluoranthene	<0.02	<0.02	
Fluorene	<0.02	<0.02	
Indeno(123-cd)pyrene	<0.02	<0.02	
Naphthalene	<0.02	<0.02	
PAH - Total	<0.005	<0.005	
Phenanthrene	<0.02	<0.02	
Pyrene	<0.02	<0.02	



Corporate Accreditation No. 1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025





Internet: [www.awqc.com.au](http://www.awqc.com.au)

Email: [producttesting@awqc.com.au](mailto:producttesting@awqc.com.au)

**FINAL REPORT**

Report ID : 311761

**Organic Compound**

Organic Compound	Blank µg/L	Test µg/L	Max Allowed
<b>Volatile Organic Compounds GCMS</b>			
1 1 1 2-Tetrachloroethane	<1	<1	
1 1 1-Trichloroethane	<1	<1	
1 1 2 2-Tetrachloroethane	<1	<1	
1 1 2-Trichloroethane	<1	<1	
1 1-Dichloropropene	<1	<1	
1 2 3-Trichlorobenzene	<1	<1	
1 2 3-Trichloropropane	<1	<1	
1 2 4-Trichlorobenzene	<1	<1	
1 2 4-Trimethylbenzene	<1	<1	
1 2-Dibromo-3-chloropropane	<1	<1	1 µg/L
1 2-Dibromoethane	<1	<1	1 µg/L
1 2-Dichlorobenzene	<1	<1	1500 µg/L
1 2-Dichloroethane	<1	<1	3 µg/L
1 2-Dichloropropane	<1	<1	
1 3 5-Trimethylbenzene	<1	<1	
1 3-Dichlorobenzene	<1	<1	
1 3-Dichloropropane	<1	<1	
1 4-Dichlorobenzene	<1	<1	40 µg/L
1,1-Dichloroethane	<1	<1	
1,1-Dichloroethene	<1	<1	30 µg/L
2,2-Dichloropropane	<1	<1	
2-Chlorotoluene	<1	<1	
4-Chlorotoluene	<1	<1	
4-Isopropyltoluene	<1	<1	
Benzene	<1	<1	1 µg/L
Bromobenzene	<1	<1	
Bromochloromethane	<1	<1	
Bromodichloromethane	26	25	60 µg/L
Bromoform	10	10	100 µg/L
Bromomethane	<4	<4	
Carbon tetrachloride	<1	<1	3 µg/L
Chlorobenzene	<1	<1	300 µg/L
Chloroethane	<4	<4	
Chloroform	17	19	400 µg/L
Chloromethane	<4	<4	
cis-1 3-Dichloropropene	<1	<1	
cis-1,2-Dichloroethene	<1	<1	
Dibromochloromethane	33	31	150 µg/L
Dibromomethane	<1	<1	
Dichlorodifluoromethane	<1	<1	
Dichloromethane	<4	<4	4 µg/L
Ethylbenzene	<1	<1	300 µg/L
Hexachlorobutadiene	<0.7	<0.7	0.7 µg/L
Isopropylbenzene	<1	<1	
m+p-Xylenes - Total	<2	<2	



Corporate Accreditation No. 1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025





Internet: [www.awqc.com.au](http://www.awqc.com.au)

Email: [producttesting@awqc.com.au](mailto:producttesting@awqc.com.au)

## FINAL REPORT

Report ID : 311761

### Organic Compound

Organic Compound	Blank µg/L	Test µg/L	Max Allowed
<b>Volatile Organic Compounds GCMS</b>			
Naphthalene	<1	<1	
n-Butylbenzene	<1	<1	
n-Propylbenzene	<1	<1	
o-Xylene	<1	<1	
sec-Butylbenzene	<1	<1	
Styrene	<1	<1	30 µg/L
tert-Butylbenzene	<1	<1	
Tetrachloroethene	<1	<1	50 µg/L
Toluene	<1	<1	800 µg/L
Total 1,2-dichloroethene	<2	<2	60 µg/L
Total 1,3-dichloropropene	<2	<2	20 µg/L
Total Trichlorobenzene	<2	<2	30 µg/L
Total Xylene	<3	<3	600 µg/L
trans-1,3-Dichloropropene	<1	<1	
trans-1,2-Dichloroethene	<1	<1	
Trichloroethene	<1	<1	
Trichlorofluoromethane	<1	<1	
Trihalomethanes - Total	86	85	250 µg/L
Vinyl chloride	<0.3	<0.3	0.3 µg/L

**Evaluation** The product passed the requirements of clause 6.8 when tested at an exposure of 15000 mm<sup>2</sup> per Litre.

**Number of Samples** 1.

**Test Comment** Subcontracted testing conducted by ALS, Environmental Division, NATA accreditation no. 825 site no. 10911 and ALS Scoresby, NATA accreditation no. 992, site no. 989

Qiong Huang

### APPROVED SIGNATORY



Corporate Accreditation No. 1115  
Chemical and Biological Testing  
Accredited for compliance with ISO/IEC 17025

